

DDP Liner

Technical data sheet

Description : **Fully recyclable** polypropylene film siliconized with silicon polymers of radical type (polymerization through U.V. irradiation).

Applications : Used as siliconized liner for all kinds of face material.

TECHNICAL CHARACTERISTICS

Property	Norm.	Unit	Value
Substance	-	gsm	31.8
Thickness	-	—	35
Tensile strength	ASTM D 882-91	N/mm ²	MD 140 TD 280
Elongation at break	ASTM D 882-91	%	MD 170 TD 50
Brightness / Glos	ASTM D 2457-90	%	90
Opacity / Haze	ASTM D 1003-00	%	1.2

Suggestions :

For the correct maintenance of the a.m. characteristics, it is recommended to observe the following criteria:

- _ storage in dry environment
- _ storage temperature between + 5° C and + 30° C
- _ a reconditioning time of at least 24h at room temperature is always recommended prior to use